



明達漆業(星)私人有限公司
Brightex Paints (Singapore) Pte. Ltd.
53 Tuas Avenue 1, Singapore 639502
TEL: 6863 5411 FAX: 6863 5411
EMAIL: enquiry53@brightexpaints.com

(Paints Manufacturer & Chemical Industrial Supplier)

Document No.: TDS-SB0012Rev01

Revised Date: 1/Nov/2016

TECHNICAL DATA SHEET FOR

Polyurethane Varnish No. 60 (Gloss/ Matt)

| | | | |
|----------------------------|---|---|------------------------------|
| Description | An air-drying type modified alkyd resin based enamel varnish | | |
| Recommended Use | Suitable for decorative finish for wood surfaces | | |
| Finish | Gloss/ Matt | | |
| Characteristics | <ul style="list-style-type: none">• Easy Application• Excellent abrasion resistance• Good durability | | |
| Technical Data | Specific Gravity (25°C) | : | 0.90 ± 0.10 |
| | Flash Point | : | 38°C |
| Application Data | Application Method | : | Spray, Brush or Roller |
| | Thinner | : | Turpentine |
| | Thinning Ratio | : | 0 - 20 % by volume |
| | Theoretical Coverage | : | Approx. 10 m ² /L |
| | Dry Film Thickness | : | Approx. 20 microns |
| | Drying Time | : | Touch Dry : Approx. 1 h |
| | | : | Hard Dry : Approx. 4 – 6 h |
| Directions of Use | Ensure surface is smooth, clean and dry. Sand to ensure a smooth surface and remove any previous coating or treatment (e.g. wax or grease). Remove all dust from sanding. Apply 2 – 3 coat(s) of Polyurethane Varnish No. 60. (with light sanding between each coat). Allow it to dry for at least 6 hours between coats. | | |
| Storage | Should be tightly sealed and stored in cool, dry place. Keep away from open flames. | | |
| Packaging | 1L, 5L | | |
| Handling and Safety | As it contains solvent, the product requires special care in handling. Avoid any eye and skin contact. For further information please refer to SDS. | | |
| Disclaimer | The information provided on this data sheet is not intended to be complete and is provided as general advice only. It is the responsibility of the user to ensure that the product is suitable for the purpose for which he/ she wishes | | |



明達漆業(星)私人有限公司
Brightex Paints (Singapore) Pte. Ltd.
53 Tuas Avenue 1, Singapore 639502
TEL: 6863 5411 FAX: 6863 5411
EMAIL: enquiry53@brightexpaints.com

(Paints Manufacturer & Chemical Industrial Supplier)

Document No.: TDS-SB0012Rev01

Revised Date: 1/Nov/2016

TECHNICAL DATA SHEET FOR

Polyurethane Varnish No. 60 (Gloss/ Matt)

to use it. As we have no control over the treatment of the product, the surface preparation, application or other factors affecting the use of the product, we are not responsible for its performance, nor would we accept any liability whatsoever or howsoever arising from the use of the product. The information contained in this data sheet may be modified by us from time to time, and without notice, in light of our experience and product development.