

(Paints Manufacturer & Chemical Industrial Supplier)

TECHNICAL DATA SHEET FOR

Betex Patina Finish

Document No.: TDS-SB0028Rev01 Revised Date: 1/Nov/2016

Description	A thermoplastic acrylic based patina colour paste	
Recommended Use	To achieve a patina effects on wrought iron, steel and various substra	ates
Characteristics	Fast DryingGood adhesionExcellent applicability	
Colour	Refer to Betex Patina Finish Colour chart	
Technical Data	Specific Gravity (25°C) : 1.06 ± 0.05 Flash Point : 60°C	
Application Data	Application Method : Brush using a thin bristles brush Thinner : Thinner Thinning Ratio : Approx. 0 - 5 % by volume	
Directions of Use	Ensure surface is smooth, clean and dry. Sand to ensure a smooth surface and remove any previous coating or treatment (e.g. wax or grease). Remove all dust from sanding. Apply 1 coat of Betex Etching Primer. Apply 1 coat of Betex Black Etching Primer No. 21. Allow it to dry thoroughly. Create the Patina effect using Betex Patina Finish. Apply 1 -2 coat of Betex Gloss Finish No. 31.	
Storage	Should be tightly sealed and stored in cool, dry place. Keep away from open flames.	
Packaging	250 ml	
Handling and Safety	As it contains solvent, the product requires special care in handling. Avoid any eye and skin contact. For further information please refer to SDS.	
Disclaimer	The information provided on this data sheet is not intended to be cor and is provided as general advice only. It is the responsibility of the usensure that the product is suitable for the purpose for which he/ she was to use it. As we have no control over the treatment of the product surface preparation, application or other factors affecting the use	user to wishes ct, the



(Paints Manufacturer & Chemical Industrial Supplier)

TECHNICAL DATA SHEET FOR

Betex Patina Finish

Document No.: TDS-SB0028Rev01 Revised Date: 1/Nov/2016

product, we are not responsible for its performance, nor would we accept any liability whatsoever or howsoever arising from the use of the product. The information contained in this data sheet may be modified by us from time to time, and without notice, in light of our experience and product development.